

## AMCOL AccoForm WA

<b>General Description</b>	High purity sodium montmorillonite, selectively mined, consisting of micronized particles and supplied as a free-flowing powder.		
<b>Functional Use</b>	This high purity montmorillonite is specially mined for use as a drainage, retention, and formation aid in the manufacture of paper products, esp. fine paper grades. Best performance is achieved when used in combination with a medium to high molecular weight cationic or non-ionic flocculant.		
<b>Purity</b>	Principally composed of the clay mineral montmorillonite. Contains minor amounts of quartz, calcite, and mica.		
<b>Solubility</b>	Insoluble in water or alcohol. One gram of clay produces a surface area greater than 750 sq. meters when fully dispersed.		
<b>Moisture</b>	7 - 14% as shipped	<b>Texture</b>	Soft, slippery
<b>Odor</b>	None	<b>Taste</b>	None
<b>CEC</b>	Typically 110 meq/100g	<b>Settleable</b>	15% maximum
<b>Dry Brightness (ISO TAPPI)</b>	> 72	<b>pH</b>	9.5 – 11.5 @ 5% solids
<b>Wet Particle Size</b>	Minimum 99.9% finer than 325 mesh (44 microns).		
<b>Dry Particle Size</b>	Minimum 98.0% finer than 325 mesh (44 microns).		
<b>Chemical Formula</b>	Diocahedral smectite, an expanding layer silicate: $(\text{Na,Ca})_{0.33}(\text{Al}_{1.67}\text{Mg}_{0.33})\text{Si}_4\text{O}_{10}(\text{OH})_2 \cdot n\text{H}_2\text{O}$		
<b>Packaging</b>	5-ply multi-wall poly-lined bags 25kg net, or 1,000kg net jumbo bags.		

The information and data contained herein are believed to be accurate and reliable. AMCOL Paper Technologies makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.