

Revised January 2009

## AccoPure<sup>®</sup> E

<b>General Description</b>	AccoPure <sup>®</sup> E is a selectively mined sodium-activated montmorillonite which has been finely milled and is supplied as a free-flowing powder.		
<b>Functional Use</b>	This montmorillonite is specifically mined for use as a flocculent in conjunction with polyacrylamides and other organic flocculants. The high swelling nature of the product makes it particularly suitable for use in dissolved air flotation systems of the type commonly encountered in Paper Mills.		
<b>Purity</b>	Principally composed of colloidal montmorillonite. Contains trace amounts of quartz, plagioclase, feldspar, siderite, anatase, opal, hematite and kaolinite.		
<b>Solubility</b>	Dispersible but insoluble in water or alcohol. One gram of montmorillonite produces a surface area greater than 750 sq. metres when fully dispersed.		
<b>Moisture</b>	7 - 14% as shipped	<b>Texture</b>	Soft, slippery
<b>Odour</b>	None	<b>Taste</b>	None
<b>CEC</b>	Typically 112 meq/100g	<b>pH</b>	9.5-11.0 @ 5%solids
<b>ISO TAPPI Brightness:</b>	Typically 29		
<b>Wet Particle Size</b>	Minimum 99.0% finer than 300 mesh (53 microns)		
<b>Dry Particle Size</b>	Minimum 90.0% finer than 200 mesh (75 microns)		
<b>Chemical Formula</b>	Montmorillonite, a dioctahedral smectite (expanding phyllosilicate), having an ideal composition:  (Na,Ca) <sub>0.33</sub> (Al <sub>1.67</sub> Mg <sub>0.33</sub> )Si <sub>4</sub> O <sub>10</sub> (OH) <sub>2</sub> .nH <sub>2</sub> O.)		
<b>Elemental Analysis</b>	Typical analysis – moisture free.		
	SiO <sub>2</sub> 59.44%	Na <sub>2</sub> O 3.37%	
	Al <sub>2</sub> O <sub>3</sub> 19.46%	CaO 1.30%	
	MgO 3.22%	K <sub>2</sub> O 1.13%	
	Fe <sub>2</sub> O <sub>3</sub> 9.6%		
	All metals are expressed as oxides, which are complexed in the mineral		
<b>Packaging</b>	Available in multi-wall paper bags (25kgs), 1 metric tonne big-bags or bulk.		

The information and data contained herein are believed to be accurate and reliable. AMCOL Paper Technologies makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.