

AccoSorb[®] WC

General Description	AccoSorb WC is a selectively mined, sodium-activated montmorillonite which has been finely milled and is supplied as a free-flowing powder.		
Functional Use	This montmorillonite is specially mined and modified for use as a pitch control agent to partially or wholly replace organic and inorganic pitch control agents. The specific surface area and chemical nature of the product makes it particularly suitable for passivation and adsorption of stickies and pitch particles in the stock approach system of a paper machine.		
Purity	Principally composed of colloidal montmorillonite. Contains trace amounts of quartz, feldspar, and calcite.		
Solubility	Dispersible but insoluble in water or alcohol. One gram of montmorillonite produces a surface area greater than 750 sq. meters when fully dispersed.		
Moisture	7 - 14% as shipped	Texture	Soft, slippery
Odor	None	Taste	None
CEC	Typically 110 meq/100g	pH	9.5 – 11.5 @ 5% solids
Dry Brightness (ISO TAPPI)	>70		
Wet Particle Size	Minimum 99.0% finer than 325 mesh (44 microns).		
Dry Particle Size	Minimum 98.0% finer than 200 mesh (74 microns).		
Chemical Formula	Montmorillonite, a dioctahedral smectite (expanding phyllosilicate), having an ideal composition: $(\text{Na,Ca})_{0.33}(\text{Al}_{1.67}\text{Mg}_{0.33})\text{Si}_4\text{O}_{10}(\text{OH})_2 \cdot n\text{H}_2\text{O}$		
Elemental	Typical analysis – moisture free.		
Composition	SiO ₂ 71.06 % Al ₂ O ₃ 15.49 % MgO 2.71 % Fe ₂ O ₃ 3.44 %	Na ₂ O 4.35 % CaO 2.59 % K ₂ O 0.13 %	
Packaging	5-ply multi-wall poly-lined bags 25kg net, or 1,000kg net jumbo bags.		

The information and data contained herein are believed to be accurate and reliable. AMCOL Paper Technologies makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.